



Pars Gohar Co.  
Polymers & Coatings Specialities

## Aldecure<sup>®</sup> H- 46A

A modified, cycloaliphatic polyamine low viscosit multi- purpose Epoxy/Hardner with very good chemical resistance, rapid drying and very good balance hardness and flexibility

Type

Form supplied

( Solvent free )

Usage

The Aldecure H-46A is mainly used for production of solvent-free coatings mortars and also primers. The resultant surfaces are track free and show really low yellowing on UV-irradiation. We recomand testir for suitability in spesific applications. The curing temperature should not be below 0 °C.

### Specification

Property	Value	Unit of measurment
Viscosity at 25°C	16-20	Sec
COLOR:	Max.3	—————
H-active equivalent	95	g/mol

### Other data\*

Property	Value	Unit of measurment
Density at 20° C	Approx 1.02±0.02	g/cm <sup>3</sup>
Pot life with 06 epoxy resin (100 g at 25°C)	—————	20-25 min

\*These values provide general information and are not part of the product specification.  
Shelf life: in sealed containers at room temperature, one year.